

Fabrication and Wear Studies of Blast Furnace Slag Particles Reinforced LM25 Composite for Two-Wheeler Clutch Pressure Plate

Pasala Mohan Kiran¹, D. Ravi Vikranth²

¹Student, Dept. of Mechanical Engineering, Sankethika Vidya Parisadh Engg. College, Visakhapatnam, India ²Asst. Prof., Dept. of Mechanical Engineering, Sankethika Vidya Parisadh Engg. College, Visakhapatnam, India

Abstract: Blast furnace emerges as the major waste material during production of pig iron by reduction the iron ore in the blast furnace. It comprises of many oxides. During this we have been faced enormous effort towards the blast furnace. Generally we used reinforced material for increasing wear resistance. But these are much cost. Present research work has been undertaken by this cost factor.

Keywords: Blast -furnace, reinforcement, oxides, cost

1. Introduction

A vast range of MMC materials has been conceived and studied. By far, the largest commercial volumes are for Aluminum matrix composites (AMCs), which accounts for 69% of the annual MMC production by mass. To produce these composites, both solid and liquid phase processing methods have been used; the later has the advantages that the fluidity of the metal allows for the use of a wide range of reinforcements and the capability of producing near net shaped casting. The major problem in fabricating metal matrix composites by liquid phase is the poor readability which leads to the non-uniform distribution of the particles. Vortex (liquid phase processing) technique involves incorporating of ceramic particulates into molten alloy using the rotating impeller. Normally, microceramic particles are used to improve the hardness and ultimate strength of the metal. However, the ductility of the MMCs deteriorates with high ceramic particle concentration.

2. Objectives

The present work is aimed on the utilization of abundantly available industrial waste BF Slag in useful manner by dispersing it into aluminum to produce AA356 –blast furnace slag composite. And compare the AA356 alloy and AA356 –

5% coarse and fine particle composite. Following are the objectives of the present investigation

- Synthesis of AA356 Alloy and micro composites.
- Preparation of AA356 alloy.
- Preparation of blast furnace slag powders.
- Synthesis of coarse blast furnace composites (CBFC).
- Synthesis of fine blast furnace slag composites.
- Characterization of blast furnace slag powder.

A. Characterization of aluminum blast furnace slag coarse and fine composites

- Microstructure studies (SEM EDX and XRD studies).
- Mechanical properties Studies.
- Studies on corrosion behavior of the AA356 alloy and AA356 –blast furnace slag composites.
- Wear studies



Fig. 1. Representative of balls used for making blast furnace Slag fine powder



Fig. 2. The blast furnace slag powder used for synthesis of ALBF slag composites (a) as received Condition (b) after heat treatment condition

Table 1											
Chemical composition of $Al - 4.5\%$ Cu $- 2$ Mg alloy											
Cu	Mg	Si	Fe	Mn	Ni	Pb	Sn	Ti	Zn	Al	
4.52	1.938	0.066	0.663	0.131	0.075	0.029	0.021	0.013	0.118	balance	

	Table 2												
Chemical composition of $Al - 4.5\%$ Cu $- 2$ Mg alloy													
	CaO	SiO ₂	Fe ₂ O ₃	Al ₂ O ₃	MnO	Loss on Ignition							
	39.2	40.0	1.8	13.5	0.76	0							





Fig. 3. Representative motions inside the jar of ball mill




Fig. 4. Distribution of blast furnace slag particles on sieving for the period

3. Results and discussion

A. By using tensile test, density measurement and XRD studies




Fig. 5. XRD analysis of milled for 1 h ball milled blast furnace slag

These samples are set into the XRD sample holder. Generally there are two types of sample holders, one is for characterizing the powder sample which is having dimensions of 20x20mm with 0.3mm depth and the other is for solid sample which is having a centered hole with 20x20mm. The XRD is power on and the voltage and the current values are set to standard values i.e. 40kV and 20mA. We test all the properties like hardness, stiffness, tensile stress and wear test. Collecting all the data with graphically and manually.

4. Conclusion

From the EDX analysis of composites shows that no oxygen peaks were observed in the matrix area, confirming that the fabricated composite did not contain any additional contamination from the atmosphere. This might be due to a shield of argon gas was maintained during the mechanical stirring while reinforcement addition. The hardness of the composites increased with increasing the amount of slag than the base alloy. The tensile properties like ultimate tensile strength and yield strengths were enhanced due to hard reinforced slag particles.

References

- Iwai Y., Honda T., Miyajima T., Iwasaki Y., Surappa M.K. and Xu J.F., 2000. Composites Sci. Technol. 60: 1781–1789.
- [2] Cao G., H. Konishi. And Li X., 2008. Mechanical properties and microstructure of SiC-reinforced Mg-(2,4)Al-1Si nanocomposites fabricated by ultrasonic cavitation based solidification processing, Materials Science and Engineering A 486: 357–362.
- [3] P Narayana Swami, B Nooka Raju, D Venkata Rao, and J Babu Rao, Synthesis and characterization of nano-structured fly ash: a waste from thermal power plant, International Journal of Engineering, Science and Technology vol. 2, no. 5, 2010, pp. 284-299.
- [4] Valdez, S., Campillo, B., Perez, R., Martinez, L., Garcia, A., Synthesis and microstructural characterization of Al-Mg alloy-SiC particle composite, Materials Letters, 2008, 62, 2623-2625.
- [5] B. I yurev, L.V. yureva methods for calculating the blast furnace. State scientific and technical publishing house of literature on ferrous and nonferrous metallurgy. Sverdlovsk.1961.page 211
- [6] Matsunaga, T., Kim, J.K., Hardcastle, S., Rohatgi, P.K., Crystllinity and selected properties of fly ash particles, Materials Science and Engineering- A, 2002, 325, 333-343.
- [7] J. Bevk, J. P. Harbison, and J. L. Bell, AppI. Phys. 49, 6031, (1978).
- [8] Wranglen, G., An introduction to corrosion and protection of metals, WNT, Warsazawa, 1985.
- [9] Ludwik, "Element der technologischen mechanic" Springer Verlag olt lt., Berlin, 1909.
- [10] Kurt Lange "Hand Book of Metal Forming" 1919 McGraw-Hill, Book Company New York.